




KALMATRON® KF-G

KALMATRON® KF-G is a CONCRETE REHABILITATION SPRAY for the renovation of concrete rheological features. This is achieved by spraying 0.05Lb of KF-G dissolved with 0.02GL of water per 1SF or 0.25Kg of KF-G dissolved with 1Liter of water sprayed per 1 m2 of surface. Closes shrinkage cracks with widths narrower than 1/8" or 3 mm.



At left and right are images of shrinkage cracks on colored and gray concrete surfaces, respectively. KALMATRON® KF-G is just sprayed on the surfaces.



In one hour, active bubbling and flecks appear on the sprayed areas. The filling of shrinkage cracks by KF-G begins.

In six to twelve hours new growths form inside the cracks, providing a micro sewing effect. Avoid water spills on newly repaired areas during the first three days after application.

The micro sewing process is accomplished, resulting in perfectly healed shrinkage cracks. Some shadows of discoloration may stay by both sides along the cracks for a few days more.